



Expanding Your Solutions

Corporate Headquarters
13191 Crossroads Pkwy N., Ste 325
City of Industry, CA 91746
Phone: 800.775.2362
Fax: 626.330.7598

Manufacturing Facilities
City of Industry, CA
Denver, CO
Ft. Worth, TX
Pittsburg, CA

Structural Engineering/Design
1001-A Pittsburgh Antioch Hwy
Pittsburg, CA 94565
Phone: 800.775.2362
Fax: 626.330.7598

Technical Services
13191 Crossroads Pkwy N., Ste 325
City of Industry, CA 91746
Phone: 800.416.2278
Fax: 626.249.5004

725SSTT200-54 SURE-SPAN™ RIM TRACK WITH PRE-SPACED TABS

Geometric Properties

725SSTT200-54 Sure-Span™ Rim Track is manufactured with a 2" leg/flange, in 54 mil thickness. All SSTT rim tracks have pre-punched tabs located at 12", 16", or 24" on-center configurations. SSTT rim tracks are available in 16' or 32' lengths. All CEMCO SSTT Rim-Tracks are designed to be used with structural load-bearing SSCJ SureSpan floor joists or CEMCO C-Studs/joists that are produced from hot-dipped galvanized steel in standard CP60 coating weight. CP90 is available upon special request.

Steel Thickness

| Mil Thickness | Design Thickness (in.) ¹ | Minimum Thickness (in.) ^{1,2} | Color Code (painted on ends) |
|---------------|-------------------------------------|--|------------------------------|
| 54 | 0.0566" (1.44 mm) | 0.0538" (1.37 mm) | Green |

1. Uncoated Steel Thickness. Thickness is for carbon sheet steel.
2. Minimum Thickness represents 95% of the design thickness and is the minimum acceptable thickness delivered to the job site, based on AISI S100.

ASTM's & Code Standards

- ASTM A653/A653M, A924/A924M, & A1003/A1003M, C955, C1007
- UL Classified and UL Certified (UL FUS)
- UL G556, G557, G559, G560, G565, G574, G580, G588, G595, H503, H508, P546, P561, P562
- IBC: 2012, 2015, 2018, 2021
- CBC: 2013, 2016, 2019
- AISI: S100, S200, S240

LEED v4 for Building and Design Construction

- MR Prerequisite: Construction and Demolition Waste Management Planning.
- MR Credit: Construction and Demolition Waste Management.
- MR Credit: Building Product Disclosure and Optimization – Sourcing of Raw Materials, Option 2.
- MR Credit: Building Product Disclosure and Optimization – Environmental Product Declarations, Options 1 & 2.
- MR Credit: Building Product Disclosure and Optimization – Material Ingredients, Option 1.
- MR Credit: Building Life-Cycle Impact Reduction, Option 4.

CEMCO cold-formed steel framing products contain 30% to 37% recycled steel.

- Total Recycled Content: 36.9%
- Post-Consumer: 19.8%
- Pre-Consumer: 14.4%

725SSTT200-54 Structural Properties & Load Capacities

| Dimensions | | | Gross Section Properties | | | | | | | | Torsional Properties | | | | Capacities | | | | |
|------------|-------|--------|--------------------------|-------------------------|-----------------------------------|-----------------------------------|-----------------------------------|-----------------------------------|---------------------|---------------------|----------------------|--|-----------------------------------|---------------------|------------|------------|---------|------------|------------|
| H (in) | Gauge | T (in) | Weight (plf) | Area (in ²) | I _x (in ⁴) | I _y (in ⁴) | S _x (in ³) | S _y (in ³) | R _x (in) | R _y (in) | X _o (in) | J _x 1000 (in ⁴) | C _w (in ⁶) | R _o (in) | β | Mat (k-in) | Vat (k) | Maf (k-in) | Vaf (k-in) |
| 7.363 | 16 | 0.0566 | 2.050 | 0.603 | 4.367 | 0.146 | 1.186 | 0.476 | 2.691 | 0.492 | -0.791 | 0.644 | 1.418 | 2.848 | 0.923 | 21.318 | 0.999 | 23.330 | 2.279 |

Notes:

1. The yield strength, F_y, is 33 ksi for 18 gauge and 50 ksi for 16, 14, and 12 gauge steel.
2. Rim Track slits are provided according to the spacing of joist; standard spacings are 12", 16", and 24".

Technical Services

Technical Services: 800.416.2278
Structural Engineering/Design: 925.473.9340
www.cemcosteel.com



This technical information reflects the most current information available and supersedes any and all previous publications effective April 06, 2022.

04-06-22 AT

